

Conplast SP430



constructive solutions

Superplasticising admixture

Uses

- To produce pumpable concrete
- To produce high strength, high grade concrete M30 & above by substantial reduction in water resulting in low permeability and high early strength.
- To produce high workability concrete requiring little or no vibration during placing.

Advantages

- Improved workability - Easier, quicker placing and compaction.
- Increased strength - Provides high early strength for precast concrete with the advantage of higher water reduction ability.
- Improved quality - Denser, close textured concrete with reduced porosity and hence more durable.
- Higher cohesion - Risk of segregation and bleeding minimised; thus aids pumping of concrete
- Chloride free - Safe in prestressed concrete and with sulphate resisting cements and marine aggregates.

Standards compliance

Conplast SP430 complies with IS:9103:1999 and BS:5075 Part 3. Conplast SP430 conforms to ASTM-C-494 Type 'F' and Type 'A' depending on the dosages used.

Description

Conplast SP430 is based on Sulphonated Napthalene Polymers and supplied as a brown liquid instantly dispersible in water.

Conplast SP430 has been specially formulated to give high water reductions upto 25% without loss of workability or to produce high quality concrete of reduced permeability.

Properties

Specific gravity	1.220 to 1.225 at 30°C *
Chloride content	Nil to IS:456 *
Air entrainment	Approx 1% additional air is entrained

* The uniformity parameters like specific gravity, pH, chloride content etc. will vary for specific customer requirements and mix design. Please refer our MTC issued for specific product configuration for measuring our product parameters that will be constantly and consistently administered.



**GreenPro Ecolabel
Certified by CII**

Compatibility	Can be used with all types of cements except high alumina cement. Conplast SP430 is compatible with other types of Fosroc admixtures when added separately to the mix. Site trials should be carried out to optimise dosages.
Workability	Can be used to produce flowing concrete that requires no compaction. Some minor adjustments may be required to produce high workable mix without segregation.
Cohesion	Cohesion is improved due to dispersion of cement particles thus minimising segregation and improving surface finish.
Compressive strength	Early strength is increased upto 20% if water reduction is taken advantage of. Generally there is improvement in strength upto 20% depending upon W/C ratio and other mix parameters.
Durability	Reduction in W/C ratio enables increase in density and impermeability thus enhancing durability of concrete.

Application instructions

Dosage

The optimum dosage is best determined by site trials with the concrete mix which enables the effects of workability, strength gain or cement reduction to be measured. Site trials with Conplast SP430 should always be compared with mix containing no admixture. As a guide, the rate of addition is generally in the range of 0.5 - 2.0 litres /100 kg of cementitious material depending on the mix design and the performance required.

Over dosing

An over dose of double the recommended amount of Conplast SP430, will result in very high workability and some retardation of setting time will occur. However, the ultimate compressive strength will not be impaired.

Dispensing

The measured quantity of Conplast SP430 should be added along with the gauging water. For best results, add Conplast SP430 superplasticiser in the last phase after prewetting the mix with 80% of the total water required.

Mix design

Fosroc has a dedicated advisory service on Concrete Mix Design and can be contacted if assistance is required.

Conplast SP430

Typical results

M-30 mix, Sand Zone 2 (40%), Coarse aggregate - 20 - 5mm (60%)
Cement : L&T OPC

Test Kg/m ³	Cement content Conplast SP430	Dosage of (mm)	W/c ratio	Slump	Compressive strength (N/mm ²)		
					7	7	28
Control	375	Nil	0.57	55	10	26	40
Workability increased	375	0.5L	0.57	140	11	30	43
Strength increased	375	0.5L	0.46	52	16	40	48

Estimating

Packing

Conplast SP430 is supplied in 5, 20, 200 litre and 250 kg drums.

Storage

Conplast SP430 has a minimum shelf life of 12 months when stored under normal temperatures. It should be protected from extreme temperatures and preferably stored in shade.

Precautions

Health and Safety instructions

Conplast SP430 is non-toxic. Any splashes on the skin should be washed immediately with water. Splashes on the eyes should be washed immediately with water and medical advice should be sought.

Fire

Conplast SP430 is non flammable.

Additional information

The Fosroc range of associated products include high strength cementitious, epoxy grout, polyester resin based mortar for rapid presetting of steel shims to level or for direct bedding of small base plates; Resin anchoring systems for same day anchoring of bolts in drilled holes in concrete or rock. Also available a range of products for use in construction; viz., admixtures, curing compounds, release agents, flooring systems and repair mortars.

Separate datasheets are available on these products.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

Embassy Point, No. 150,
2nd Floor, Infantry Road,
Bangalore 560 001,
Karnataka

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

+91 80-42521900

fax

+91 80-22281510

e-mail

enquiry.india@fosroc.com

Regional Offices

Chennai

Hills Centre, Old No 5,
New No 9, 3rd Cross Street,
Jeth Nagar, Raja Annamalaipuram,
Chennai 600 028.
Ph: 9500064795

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector- 62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900
Fax: 0120-4270622

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0278