

ShaliPoxy® CTE 406

2K High Build Solvent Free Modified Epoxy Coating



Description

ShaliPoxy® CTE 406 (formerly known as ShaliPoxy CTE 403) is 100% solid, fast setting, spray applied, solvent free, two component, modified epoxy coating for internal / external lining of steel / concrete surface of pipes, vessels and other equipments used for water, mild chemical, oil and lubricant spillage.

ShaliPoxy® CTE 406 is spray applied by plural component airless spray gun.

ShaliPoxy® CTE 406 is solvent free protective barrier and is ideally suited for direct to metal coat where higher film thickness is required.

It conforms to AWWA C-210, SSPC Paint 16 and Corp of Engineers C 200 / C 200a.

Characteristics – Physical

Colour	Brownish Black Glossy smooth	Ratio, volume	3:1
		Sagging Test up to 420 microns DFT in single coat	Passes
		Cross-cut test	Passes
Pot Life @ 28 OC, 55% RH, 100 g, minute	30 ± 3	Volume Solids	100 %
Specific Gravity (Mixed) @ 27°C	1.40 ± 0.05	Drying time @ 27°C, 55% RH <ul style="list-style-type: none">• Touch Dry• Hard Dry• Full Cure	Within 2 hrs. 8 - 10 hrs. 7 days
Theoretical Coverage *, m ² / L, 406 micron DFT	2.50		
Application Temperature, °C	10 - 60 with RH < 75%		

* Depending upon surface condition

Characteristics - Technical

Property	Method	Result
Tensile strength, MPa	ASTM D 638	15 ± 3
Abrasion Resistance, 1000 cycle	ASTM D 4060	< 50 mg
Adhesion pull-off, MPa <ul style="list-style-type: none">• On concrete• On Steel	ASTM D 4541	> 3 > 10
Elongation, %	ASTM D 638	10 ± 1
Water vapor transmission, 24 hrs., gm / m ²	ASTM E 96	0.10
Hardness Shore D, minute	ASTM D 2240	85 ± 5
Immersion test, 30 days <ul style="list-style-type: none">• DIW• 1% H₂SO₄• 1% NaOH	AWWA C 210	No blistering / peeling / disbanding
Scratch Resistance, 1.5 kg load	IS 101	No failure
Compressive Strength (MPa)	ASTM C 109	70 ± 5
Salt spray test, 5000 hrs.	ASTM B 117	Passes

Application

- Excellent coating for internal / external lining of pipelines where abrasion / chemical resistance is of major concern.
- Coastal environment.

- Pulp & Paper industry.
- Excellent coating for internal / external linings of water pipelines.
- Internal coating for concrete / steel water storage.
- Sea water intake tunnels.

Advantages

- Solvent free, fast setting, high build-up epoxy.
- Excellent film build capabilities exceeding 400 micron in single coat, which can be extended with multiple passes.
- Excellent chemical / abrasion resistance properties.
- Very low permeability.

Application Methodology

- **Surface Preparation**
 - Remove all loose gravel, dirt, oil, grease or other loose foreign particles by sand blasting / iron brush / compressed air.
 - Prepare surface by mechanical grinding, shot blasting conforming to SA2½.
- **Material Preparation**
 - Stir Component A thoroughly for uniformity. For best result, use a variable speed drill mixer with a spiral type blade at the bottom of stirrer rod. The speed may be 400-600 rpm.
 - Pre heat Component A @ 60 - 75°C and Component B @ 50 - 60°C.
- **Application of Material**
 - Apply **ShaliPoxy® CTE 406** by plural feed airless spray gun to the required thickness on the prepared substrate.
 - The tip pressure typically should be 2500 - 4000 psi (the tip pressure should be adjusted to achieve good atomization of the spray).
 - Tip size typically should be 27 - 35 Thou orifice.

Cleaning & Maintenance

Clean all tools immediately after use with STP cleaner.

Health & Safety

- Avoid contact with skin / eyes, and avoid swallowing.
- Ensure adequate ventilation and avoid inhalation of vapour.
- Wear suitable protective clothing, gloves and eye protection.
- In case of skin contact, rinse with plenty of clean water, then cleanse with soap and water. Do not use solvent to clean the contacted area.
- In case of eye contact, wash with plenty of clean water and seek medical advice.
- If swallowed, seek medical attention immediately. Do not induce vomiting.

Packing

Available in 200 L drum with 1 drum of Component B for every 3 drums of Component A.

Storage

Store in a cool dry place, under shade, away from heat.

Shelf Life

12 months in original, unopened, sealed condition.



STP Limited
Enhancing Structures' Life

Product Range

- Waterproofing & Insulation
- Road Surfacing
- Sealants & Adhesives
- Pipeline Coatings
- Protective/Anti-Corrosion Coatings
- Epoxy and Flooring
- Grouts and Admixtures (GARA)
- RestoFix - Repair/Rehabilitation
- Other Construction Chemicals



Advisory Cell: +91 81302 81114

www.stpltd.com